

# **TECHNICAL DATA SHEET**

# **AUTOMEL 640 (2K Urethane Primer Surfacer)**

## Description

Automel 640 is a quick drying high build urethane 2 Pack Primer Surfacer is designed to give excellent benefits such as Adhesion, Levelling, Colour/Gloss Holdout, Easy to Sand and Fill Scratch Marks.

#### **Compatible Substrates**

Properly prepared steel and alumina substrate properly applied Edgechem under coats Putties and body fillers

Wash primers and Edgechem filler

#### **Preparation**

Existing finishes -degrease, dry sand P220-p320 Polyester Filler - degrease, dry sand with P220-P320 Steel surfaces - degrease, dry sand with P220 Aluminium surfaces - degrease, apply etching primer

#### **Application**

2-3 Wet coats, allowing 10 minutes flash time

HVLP 7-8 Psi at air cap Conventional 30-35 psi at s/gun

Spray gun set up fluid tip 1.5 – 2.0 mm

Mixing			
640	<u>640</u>	<u>URETHANE</u>	
SURFACER	<b>HARDENER</b>	<b>REDUCER</b>	
4	1	1	
Pot life -	2 hours @ 27 Ĉ		

**Dry Times** 

Dust free - 5-10 minutes @27\_C

Flash time 10 minutes @27 °C
Dry to Handle 1 hour @ 27 °C
Dry to sand 2 - 3 hours @ 27 °C

## Clean Up

Clean spray gun, mixing cup etc., thoroughly with Edgechem Lacquer Thinner, Edgechem Urethane Reducer or any other appropriate clean up solvent after each use.

Please follow relevant agency guidelines for proper storage and disposal of solvent-borne paint. See MSDS for this product for further instructions.

# **Properties**

VOC 293 g/l OR 2.44 lbs/gal

Shelf life 2 years

Viscosity CP: 1000-1300

Coverage per coat 20 m<sup>2</sup>/l

Colour Yellowish Grey

Flash point 35<sub>.</sub>C

Density 11.5 – 12.5 lb/gal

#### Limitations

Edgechem products should not be combined with components of other product lines.

#### **Precautionary Information:**

The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have hazards of all its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

## Medical Response:

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (876)937-3831-4

#### Material Safety Data Sheet:

Material safety data sheet for the Edgechem products named herein can be obtained from Edgechem Jamaica Limited by emailing researchanddev@edgechem.com