

EDGECHEM JAMAICA LIMITED

18 Carifta Avenue Kingston 11, Jamaica

Rev. 2

Tel: (876) 937-3831-4 Fax: 937-3838

E-mail: edge@cwjamaica.com

www.edgechem.com

.D.S

PRODUCT DATA

EDGECOLAC (Chinese Lacquer)

DESCRIPTION

Edgechem Edgecolac Chinese lacquer is a tough, high gloss medium/long oil alkyd maintenance enamel. It is suitable for interior and exterior use on metal and wood. Edgecolac Chinese lacquer is free of lead, chromate and other toxic heavy metals making it suitable for use on cribs, toys and children furniture.

PERFORMANCE FEATURES

- **Tough Finish**
- **High Gloss**
- Low toxicity
- **Interior and exterior use**
- **Excellent gloss retention and durability**

PHYSICAL PROPERTIES

Gloss >85% at 60° **Viscosity** 90-100s **Specific Gravity** 0.96-1.11

Flash Point 25-28°C (based on major solvent component)

Color White, Black, Customer Specified

Coverage 380-400 sq.ft.

Drying Time

Dust Free 10-15 minutes **Tack Free** 30-45 minutes

Dry to Handle 4 hours Hard dry 24 hours **Recoat time** 12 hours

01/2013

EDGECHEM JAMAICA LIMITED

TECHNICAL DATA PAGE 2

EDGECOLAC (Chinese Lacquer)

SUGGESTED USES

For use on steel, masonry, wood, galvanized steel and aluminum.

SURFACE PREPARATION

Clean surface free of dirt, oil, flakes or loose paint. Galvanized steel and alumimium must be primed with an etching or epoxy primer.

For wood and masonry, sand using 180g sandpaper, remove dust and flake.

Reduce with Oil Paint Thinner if necessary

APPLICATION

Spray or brush 2 coats allowing 5 minutes for flash off between coats. Spraying Pressure is 35-40 psi.

SHELFLIFE

2 Years

CLEAN UP

Clean up with Edgechem Oil Paint Thinner

01/2013