



EDGECHEM JAMAICA LIMITED  
18 Carifta Avenue  
Kingston 11, Jamaica  
Tel: (876) 937-3831-4 Fax: 937-3838  
E-mail: [edge@cwjamaica.com](mailto:edge@cwjamaica.com)  
Website: [www.edgechem.com](http://www.edgechem.com)

## PRODUCT DATA SHEET

Rev. 0

T.D.S.

### EDGESPIRIT TINTING SYSTEM

#### DESCRIPTION

Edgechem Edgespirit is a point of sale tinting system available at select locations. It is formulated from high quality base paints using universal colorants. It offers a selection of over one thousand professionally designed colours to make a professional statement inside and outside your home. Choose from the Edgespirit Portfolio Pro fandeck and have your colour mixed in Flat Emulsion, Low sheen Emulsion or Gloss oil from the EDGESPIRIT Tinting System.

#### PERFORMANCE FEATURES

- Interior & exterior durability
- Non-toxic
- Resistant to fungus and mildew
- Low odour
- Easy application
- Excellent color retention

#### PHYSICAL CHARACTERISTICS

Colour : See Edgespirit Portfolio Pro Fandack  
Finish : Available in Flat Emulsion, Low Sheen Emulsion, Gloss Oil  
Drying Time  
(31° and 70% RH) : Dependent on temperature and relative humidity:

##### **Flat and Low Sheen Emulsion**

To Touch : approximately 15 minutes  
To Recoat : after 1 hour

##### **Gloss Oil**

To Touch : 4 hours  
To Recoat : 24 hours

## **EDGESPIRIT TINTING SYSTEM**

### **COVERAGE RATE**

Approximately 400 ft<sup>2</sup>/gallon (38 m<sup>2</sup>) at 1.5 mils DFT dependent on surface porosity.

### **SURFACE PREPARATION**

Surface must be free of dirt, grease, wax, rust, mildew, fungus, chalk, peeling paint and all other foreign substances. Glossy surface should be sanded. For Flat and Low sheen Edgespirit colours check adhesion to suspected alkyd or oil paint in an area prior to applying latex coatings. If an adhesion problem is present, prime with a suitable primer to form an intermediate coat.

New or unpainted surfaces should be cured properly then coated with an appropriate primer before application of Edgespirit topcoat.

### **APPLICATION**

Stir thoroughly before application. If using a brush or roller no reduction is required – use full body. If necessary, thin Edgespirit Flat and Low Sheen Emulsion with water, no more than ½ pint per gallon. If spraying, reduction of up to 1 pint of water per gallon is allowed.

If spraying Edgespirit Gloss oil reduce by 10% using Edgechem Oil Paint Reducer (1 pint reducer to 1 gallon paint). Paint spatters or drops must be cleaned immediately with the reducer.

### **SHELF LIFE**

Edgespirit Flat and Low Sheen	-	2 year
Edgespirit Gloss Oil	-	3 Years

### **CLEAN-UP**

This should be done immediately after painting.

For Edgespirit Flat and Low Sheen Emulsion wash out brushes and rollers with clean water.

For Edgespirit Gloss Oil clean brushes, roller and spray equipment using Edgechem Oil Paint Reducer